



(82) 31-321-4400, Fax. (82) 31-321-4407

Simigok-ro 37, Idong-myeon, Yongin-si, Gyeonggi-do, 17130 S.Korea

## Technical Data Sheet

Rev.0. 18.10.18.

### APET013 - APET/PE/EVOH/PE Laminate (Peelable) (100% virgin APET film laminated with 7my EVOH & PE PE/EVOH/PE) DEEP DRAW HIGH OXYGEN BARRIER FOOD GRADE

APET is the favored food packaging film worldwide with excellent clarity.  
 APET is fully recyclable, easily formed & imparts excellent barrier properties in food packaging applications and has a small carbon footprint. PE film is FDA grade suitable for both food contact & sealing layer for lidding. EVOH is an ultra high oxygen barrier for extended shelf life for food packaging.

#### PHYSICAL PROPERTIES

Property	Unit	Nominal Value	Test Method
Specific gravity (APET)	g/cm <sup>2</sup>	1.34	ASTM D 1503
Specific gravity (PE)	g/cm <sup>2</sup>	0.95	ASTM D 1503
Tensile strength	kg/m <sup>2</sup>	325	ASTM D 882
Izod impact strength * @23°C ( 73°F )	J/m <sup>2</sup>	45	ASTM D 256
Heat distortion temp. * @0.455mpa ( 66 psi )	°C	65-70	ASTM D 648
Vicat softening point (@ 5kg load)	°C	71 (+/-2)	ASTM D 1525
Thermoforming Temp.	°C	125-150	ASTM D 1003
Peel Strength	N	8N/15mm	Inhouse INSTRON

#### BARRIER PROPERTIES

Oxygen barrier	cc	<- 1.2cc/m2/24hr atm	ASTM D 3895
CO2 barrier	cc	<- 5cc/m2/24hr atm	ASTM D 3895

#### GENERAL SPECIFICATIONS

- Maximum 80% post-consumer recycled content
- Surface silicone & internal antiblock/corona treatment on request
- Antifog & Antistatic coatings on request
- Gauges from 150micron to 1.4mm thickness
- Average max. roll width : 1,800mm
- No black specks  $\geq 0.8m^2$
- Standard core diameter 76mm or 152mm

#### CERTIFICATIONS

- USFDA CFR 21 : SECTION 177.1630
- BRC British Retail Consortium
- CONEG limits on heavy metal content
- ISO 9001/14001
- SGS REACH
- SGS EU 94/62

All data is based on in-house testing and are believed to be typical values when measured under laboratory condition.

Actual performance of the product described here in, and suitability for use is the responsibility of an end user.